



RubberGard Non-Reinforced EPDM Membrane (Black)

DESCRIPTION:

Firestone RubberGard non-reinforced EPDM Membrane is a cured single-ply roofing membrane.

PREPARATION OF SUBSTRATES:

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All roughened surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than 1/4" (6.3 mm) wide shall be properly filled with an acceptable fill material.

METHOD OF APPLICATION:

1. RubberGard non-reinforced EPDM Membrane must be installed in accordance with current RubberGard specifications, details and workmanship requirements. It can be used in ballasted, fully adhered and mechanically attached systems.

STORAGE:

1. Store away from sources of punctures, and physical damage.
2. Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
3. Store away from ignition sources as membrane will burn when exposed to open flame.

This sheet is meant only to highlight Firestone's products and specifications. Information is subject to change without notice. Firestone takes responsibility for furnishing quality materials, which meet Firestone's published product specification. As neither Firestone itself nor its representatives practice architecture, Firestone offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure, or its ability to support a planned installation properly, the Owner should obtain opinions of competent structural engineers before proceeding. Firestone accepts no liability for any structural failure or for resultant damages, and no Firestone Representative is authorized to vary this disclaimer.

PRODUCT DATA

PACKAGING:

Thickness	Widths	Lengths	Weight
.045" (1.1 mm)	7.5 ft* (2.3 m*)	50 ft (15.2 m)	0.29 lb/sf (1.4 kg/m ²)
	9 ft** (2.7 m**)	100 ft (30.5 m)	
	10 ft (3 m)	200 ft (61 m)	
	20 ft (6.1 m)		
	25 ft (7.6 m)		
.060" (1.5 mm)	7.5 ft* (2.3 m*)	50 ft (15.2 m)	0.40 lb (1.9 kg/m ²)
	9 ft** (2.7 m**)	100 ft (30.5 m)	
	10 ft (3 m)		
	20 ft (6.1 m)		

*Packaged 2 panels per roll.

**Available in 100' (30.5 m) rolls only.

PRECAUTIONS:

1. Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
2. Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane. Contact Firestone Roofing System Solutions Department for specific recommendations.
3. Refer to Material Safety Data Sheets (MSDS) for safety information.

LEED INFORMATION:

Post Consumer Recycled Content:	0%
Post Industrial Recycled Content:	0%
Manufacturing Locations:	Prescott, AR Kingstree, SC



Subject to the conditions of Approval when installed as described in the current edition of the FM Approval Guide



Membrane for Roofing Systems
As to an External Fire Exposure Only
61P2
See UL Directory of Products
Certified for Canada
And UL Roofing Materials
And Systems Directory
R9516

Firestone Building Products Company
A Division of BFS Diversified Products, LLC
310 E. 96th Street, Indianapolis, IN 46240
Sales: (800) 428-4442 • Technical (800) 428-4511
www.firestonebpc.com



RubberGard Non-Reinforced EPDM Membrane (Black)

PHYSICAL PROPERTIES

<u>Property</u>	<u>Test Method</u>	<u>Minimum ASTM Performance</u>	<u>Typical Values</u>
Thickness, min			
Sheet-overall	ASTM D 412	0.0405 in (1.028 mm)	0.043 in (1.092 mm)
Tensile strength, min	ASTM D 412 (Die C)	1305 psi (9.0 MPa)	1425 psi (9.8 MPa)
Elongation, ultimate, min	ASTM D 412 (Die C)	300%	450%
Tensile set, max	ASTM D 412 Method A, (Die C)	10%	5%
Tear resistance, min	ASTM D 624 (Die C)	150 lbf/in (26.3 kN/m)	200 lbf/in (35.0 kN/m)
Brittleness point, max	ASTM D 2137	-49° F (-45° C)	-63° F (-53° C)
Ozone resistance, no cracks	ASTM D 1149	pass	pass
Heat Aging:	ASTM D 573		
Tensile strength, min	ASTM D 412 (Die C)	1205 psi (8.3 MPa)	1415 psi (9.7 MPa)
Elongation, ultimate, min	ASTM D 412 (Die C)	200%	290%
Tear resistance, min	ASTM D 624 (Die C)	125 lbf/in (21.9 kN/m)	180 lbf/in (31.5 kN/m)
Linear dimensional change, max	ASTM D 1204	±1.0 %	-0.7%
Water absorption, max, mass %	ASTM D 471	+8, -2%	+1.8%
Factory seam strength, min	ASTM D 816, Method B 50 lbf/in (Modified)	(8.8 kN/m) or sheet failure	sheet failure
Weather resistance:			
Visual inspection	ASTM D 518	pass	pass
PRFSE, min	ASTM D 518	30%	63%
Elongation, ultimate, min	ASTM D 412 (Die C)	200%	290%

RubberGard membrane meets or exceeds the minimum requirements set forth by ASTM D 4637, and CGSB 37-GP-52M, for Type I, Class A, non-reinforced EPDM single-ply roofing membranes.