



QuickSeam Corner Flashing

Firestone Item Number: W56RAC1646

DESCRIPTION:

QuickSeam Corner Flashing consists of Firestone FormFlash factory laminated to QuickSeam Tape. It is 8.5" (216 mm) in diameter and is designed to flash inside and outside corners of EPDM Roof Systems.

METHOD OF APPLICATION:

1. Use QuickPrime Plus and a QuickScrubber or QuickScrubber Plus pad and handle to clean and prime mating surfaces. Refer to Firestone Installation Instruction Sheet for QuickSeam Corner Flashing (included in each carton) and Firestone Specifications and Details.
2. When cloudy conditions below 60° F (15.6° C) occur, use heat guns (without ignition sources) to heat QuickSeam Corner Flashing. This will ensure good formability of the QuickSeam Corner Flashing to the primed substrate.
3. On sunny days less than 70° F (21.1° C), place QuickSeam Corner Flashing on roof (prior to application) with flashing side up to allow QuickSeam Corner Flashing to warm to ensure good formability.
4. On sunny days greater than 70° F (21.1° C), place QuickSeam Corner Flashing on roof (prior to application) with release paper side up to prevent QuickSeam Corner Flashing from gaining too much heat and to ensure good formability.

QuickSeam Corner Flashing is used and is covered by U.S. Patent No. 5,804,661

PACKAGING:

20 Corner Flashings per carton
100 cartons per pallet

This sheet is meant only to highlight Firestone's products and specifications. Information is subject to change without notice. Firestone takes responsibility for furnishing quality materials, which meet Firestone's published product specification. As neither Firestone itself nor its representatives practice architecture, Firestone offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure, or its ability to support a planned installation properly, the Owner should obtain opinions of competent structural engineers before proceeding. Firestone accepts no liability for any structural failure or for resultant damages, and no Firestone Representative is authorized to vary this disclaimer.

PRODUCT DATA

QUICKSEAM TAPE

<u>Property</u>	<u>Minimum Performance</u>
Base:	Rubber Polymer
Color:	Black
Solvents:	None
Percent Solids:	100%
Cure State:	Cured
Thickness:	.025" ± .005" (.64 mm ± .13 mm)

FORMFLASH

<u>Property</u>	<u>Minimum Performance</u>
Base:	EPDM
Color:	Black
Solvents:	None
Percent Solids:	100%
Cure State:	Uncured
Thickness:	.065" ± .005" (1.59 mm ± .13 mm)

SHELF LIFE:

1. Shelf life of 6 months can be expected when stored at 60° F (15.6° C) and 80° F (26.7° C) in original unopened containers indoors.
2. Shelf life will be shortened if exposed to elevated temperatures.

STORAGE:

1. Store in original unopened cartons at temperatures between 60° F (15.6° C) and 80° F (26.7° C).
2. Do not store on roof in direct sunlight or at temperatures above 80° F (26.7° C).
3. When exposed to lower temperatures, restore to room temperature prior to use.

LEED INFORMATION

Post Consumer Recycled Content:	0%
Post Industrial Recycled Content:	0%
Manufacturing Location:	Michigan Center, MI Prescott, AR

Firestone Building Products Company

A Division of BFS Diversified Products, LLC
310 E. 96th Street, Indianapolis, IN 46240
Sales: (800) 428-4442 • Technical (800) 428-4511
www.firestonebpco.com