



## Splice Wash SW-100

**Firestone Item Number: W563587066**

**DESCRIPTION:**

Splice Wash SW-100 is designed to clean and prepare Firestone single-ply membranes to receive adhesives where required by Firestone Specifications and Details.

**METHOD OF APPLICATION:**

Apply Splice Wash to the splicing area using a clean, white, natural fiber rag. Use a scrubbing motion until the splicing surface is clean of dirt and debris. Additional attention must be given to factory seams and where other excess accumulations of dusting agent occur. Allow the washed surfaces to dry until the solvent's sheen is gone. This is usually between 10-30 minutes and may vary with ambient weather conditions. Membrane is clean when it is uniformly dark gray in color without streaks.

**COVERAGE RATE:**

1. Coverage rate of 200-250 square feet per gallon (4.9 - 6.1 sq. m/L) (one side)

**STORAGE:**

1. Store in original unopened pails indoors at temperatures between 60° F (16° C) and 80° F (26.7° C) away from all sources of direct heat and ignition - this is a flammable liquid.
2. When exposed to lower temperatures, restore to room temperature prior to use.
3. Keep the material out of direct sunlight until ready for immediate use.

**SHELF LIFE:**

1. Shelf life of one year can be expected if stored in original unopened pails at temperatures between 60° F (16° C) and 80° F (26.7° C).

This sheet is meant only to highlight Firestone's products and specifications. Information is subject to change without notice. Firestone takes responsibility for furnishing quality materials, which meet Firestone's published product specification. As neither Firestone itself nor its representatives practice architecture, Firestone offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure, or its ability to support a planned installation properly, the Owner should obtain opinions of competent structural engineers before proceeding. Firestone accepts no liability for any structural failure or for resultant damages, and no Firestone Representative is authorized to vary this disclaimer.

### PRODUCT DATA

<u>Property</u>	<u>Minimum Performance</u>
Solvents:	Aliphatic Hydrocarbon Mixture
Viscosity:	Very thin, free flowing
Weight per Gallon:	6.3 lb/gal (.75 kg/L)(nominal)
Specific Gravity:	.75 (nominal)
Flash Point:	55° F (12.8° C)
Boiling Point:	247° F (119.4° C)
Volatile Organic Compound (V.O.C.)	
Content:	6.21 lb/gal (745 gm/L)

**PRECAUTIONARY DATA:**

1. Thinning is not allowed.
2. Flammable Liquid. Store and use away from all sources of direct heat and ignition. Keep containers closed when not in use.
3. Use of solvent-resistant Neoprene gloves is required when applying Splice Wash. Do not allow Splice Wash to come in direct contact with skin.
4. Avoid breathing vapors.
5. Refer to Material Safety Data Sheet (MSDS) for additional precautionary data.
6. Do not use as a pre-wash for any QuickSeam Tape products. QuickPrime Plus must be used for QuickSeam Tape products.
7. Refer to the Technical Information Sheet titled "Recommended Guidelines For Application Of Adhesive To Occupied Buildings".

**LEED INFORMATION:**

Post Consumer Recycled Content: 0%  
 Post Industrial Recycled Content: 0%  
 Manufacturing Location: South Bend, IN

**Firestone Building Products Company**  
 A Division of BFS Diversified Products, LLC  
 310 E. 96<sup>th</sup> Street, Indianapolis, IN 46240  
 Sales: (800) 428-4442 • Technical (800) 428-4511  
[www.firestonebpc.com](http://www.firestonebpc.com)